

AMENDMENTS TO THE CLAIMS

Please amend the claims as follows:

1-20. (Cancelled)

21. (Currently Amended) A pressure-sensitive adhesive material or a sealing material which has a three-dimensional structure and a defined cross-sectional contour, wherein said material is produced by polymerization of a polymerizable mass comprising at least one compound selected from the group consisting of aromatic (meth)acrylates, alicyclic (meth)acrylates, polycyclic (meth)acrylates, heterocyclic (meth)acrylates, di-, tri- and higher (meth)acrylates, epoxide acrylates, epoxides, vinyl ethers, vinyl esters, and styrene,

wherein said material is present in a form of strings, strands or strips having a round, semicircular, oval, elliptical, triangular, quadrangular, polygonal or irregular cross-sectional contour and a thickness of 0.5 to 50 mm.

22. (Previously Presented) The material according to claim 21, wherein the compound is selected from the group consisting of benzyl (meth)acrylate, phenyl (meth)acrylate, phenoxyethyl (meth)acrylate, tetrafurfuryl (meth)acrylate, and isobornyl (meth)acrylate.

23. (Previously Presented) The material according to claim 21, wherein the compound is selected from the group consisting of hexanediol di(meth)acrylate, trimethylolpropane tri(meth)acrylate, pentaerythritol tetra(meth)acrylate, hydroxyethyl (meth)acrylate, and 2-aminoethyl (meth)acrylate.

24. (Previously Presented) The material according to claim 21, wherein the vinyl ester is vinyl acetate.

25. (Cancelled)

26. (Previously Presented) The material according to claim 21, wherein the epoxide is based on bisphenol A.

27. (Previously Presented) The material according to claim 21, wherein the epoxide acrylate is a homopolymer of glycidyl (meth)acrylate.

28. (Previously Presented) The material according to claim 21, wherein the polymerizable mass comprises 0.5 to 5 %-wt. of a radiation-sensitive initiator.

29. (Previously Presented) The material according to claim 28, wherein the radiation-sensitive initiator is selected from the group consisting of 2-hydroxy-2methyl-1-phenyl-1-propanone, 1-hydroxy-cyclohexyl-phenyl-ketone, iodonium, (4-methylphenyl)[4-(2-methylpropyl)-phenyl]hexafluorophosphate(1-), 2-benzyl-2-(dimethylamino)-1-[4-(4-morpholinyl)phenyl]-1-butanone, a mixture of 50%-wt of 1-hydroxy-cyclohexyl-phenyl-ketone and 50%-wt of benzophenone, bis [2,6-difluoro-3-(1H-pyrrol-1-yl)phenyl]titanium, phosphine oxide phenyl-bis-(2,4,6-trimethyl benzoyl and 2-hydroxy-1-[4-2(hydroxyethoxy)phenyl]-2-methyl-1-propanone.

30. (Previously Presented) The material according to claim 21, wherein the polymerizable mass comprises 0.1 to 10 %-wt. of at least one inorganic filler.

31. (Previously Presented) The material according to claim 21, wherein the polymerizable mass comprises 0.1 to 10 %-wt. of at least one flame-proofing agent.

32. (Previously Presented) The material according to claim 21, wherein the polymerizable mass comprises 0.1 to 2 %.wt. of at least one colorant.

33. (Previously Presented) The material according to claim 21, wherein the polymerizable mass comprises 0.05 to 55 %-wt. of at least one cross-linking agent.

34-35. (Cancelled)

36. (Withdrawn) A method of permanently or releasably adhesively bonding of objects, comprising the step of:

applying the pressure sensitive adhesive materials according to claim 21 between the objects to be bonded.

37. (Withdrawn) A method of sealing joints or flanged joints or panes, comprising the step of:

applying the sealing materials according to claim 21 to the joints or the flanged joints or the panes to be sealed.

38. (Previously Presented) The material according to claim 21, wherein the material is present as rolled or continuous material.

39. (New) The material according to claim 21, wherein said strings, strands, or strips have a thickness of 0.5 to 10 mm.

*Application No. 10/799,724
Amendment dated January 16, 2008
Reply to Office Action of September 19, 2007*

*Docket No.3868-0156P
Art Unit: 1771
Page 6 of 11*

40. (New) The material according to claim 21, wherein a ratio of width to height of said strings, strands, or strips having a quadrangular cross-sectional contour is a range of 1:1 to 1:3.